

Product Data Sheet

PUROLITE® A860

Softening & Industrial Water

Macroporous Strong Base Anion Exchange Resin

Purolite A860 is a macroporous type 1 strong base anion exchange resin with an acrylic matrix. The acrylic matrix ensures excellent removal of organic matter from a water supply in conjunction with their reversible removal upon regeneration. This resin is regenerated very efficiently with lower levels of sodium hydroxide than those required for a polystyrene based type 1 resin, and yet it has a comparable ability to remove weaker acids including carbonic acid and silica. Its use in combination with a polystyrene based resin (for instance in a mixed bed positioned after the anion unit) can often result in the removal of a wider spectrum of organic compounds than either type of anion resin alone, and is particularly resistant to organic fouling, even where loadings are relatively high.

Basic Features:

Application Decolourisation of Organic Solutions (Sugar Syrups). Organic

Scavenger.

Polymer Structure Macroporous polyacrylic crosslinked with divinylbenzene

Appearance Spherical beads

Functional Group Quaternary Ammonium

Ionic form as shipped

Product Data:

Total Capacity (min.)	Cl	0.80 eq/l
Total Capacity (min.)	Cl	17.47 kGr/ft ³
Moisture Retention	Cl	66-72 %
Mean Size Typical		0.60-0.85 mm
Uniformity Coefficient (max.)		1.70
Irreversible Swelling (max.)		10
Reversible Swelling (max.)	$CI^- \rightarrow OH^-$	20 %
Specific Gravity		1.08 g/ml
Shipping Weight (approx.)		680-730 g/l
Shipping Weight (approx.) Temp Limit	OH ⁻	680-730 g/l 40 °C
	OH-	
Temp Limit		40 °C
Temp Limit Temp Limit	OH-	40 °C 104 °F

Telephone: (1) 610-668-9090 Fax: (1) 610-668-8139

USA

Email: info@puroliteusa.com

Europe

Telephone: +44 1443 229334

Fax: +44 1443 227073

Email: sales@purolite.com

Asia Pacific

Telephone: +86 571 876 31385 Fax: +86 571 876 31385

Email: pultalan@purolitechina.com



Product Data Sheet

PUROLITE® A860 Softening & Industrial Water

pH Limits H^+ 1-14 (Operating)

USA

Telephone: (1) 610-668-9090 Fax: (1) 610-668-8139 Email: info@puroliteusa.com Europe

Telephone: +44 1443 229334 Fax: +44 1443 227073 Email: sales@purolite.com Asia Pacific

Telephone: +86 571 876 31385

Fax: +86 571 876 31385

Email: pultalan@purolitechina.com